



## 100% Recycled Natural Kraft

		Grade	25	28	30	33	35	38	40	45	48	50	55	57	60	63	65	70
Property		Units																
Basis Weight	Target	lbs/3000 sq. ft.	25	28	30	33	35	38	40	45	48	50	55	57	60	63	65	70
	Range		23.8-26.3	26.6-29.4	28.5-31.5	31.4-34.7	33.3-36.8	36.1-39.9	38-42	42.8-47.8	45.6-50.4	47.5-52.5	52.3-57.3	54.2-59.9	57-63	59.9-66.2	61.8-68.3	66.5-73.5
Moisture	Target	%	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6
	Range	%	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5	4.5-8.5
Caliper	Target	mils	3	3.3	3.6	3.9	4.1	4.3	4.5	5.2	5.3	5.3	6.1	6.2	6.3	6.5	6.8	7.5
Mullen	Target	psi	9	10	15	15	17	20	22	25	26	27	31	33	34	35	36	37
	Minimum		7	8	12	12	14.5	17	17	22	23	23	24	24	25	26	27	33
MD Tear	Target	gf	40	40	47	47	52	59	62	66	70	78	86	90	93	94	96	125
	Minimum		30	31	32	32	47	52	57	58	59	66	69	72	81	82	83	120
CD Tear	Target	gf	48	50	63	63	70	75	82	86	90	100	115	120	130	132	135	138
	Minimum		35	40	41	45	60	65	67	67	70	86	101	108	114	117	117	120
MD Tensile	Target	lbsf/in	10	11	15	16	18	18	22	25	26	27	30	31	32	33	34	38
	Minimum		8	9	14	14	17	17	18	23	23.5	24	28	28	29	29	30	33.5
Cobb	Target	g/m2	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	40
Porosity	Target	sec	6	5	8	11	14	15	15	18	19	20	22	22	23	24	24	24

Revised 5/1/19

Information contained within this document is accurate to the best of our knowledge. This is intended to show the typical range of paper properties.

UP Paper does not make any claims of particular use or regulations with and by this specification sheet. Information contained within is subject to change without notice

FSC® Recycled 100% NC-COC-007478, 100% PEFC™ Certified PwC-PEFC-497

SFI® 100% Certified Sourcing PwC-SFIL-497, 100% Recycled Content PwC-SFICoC-497